



Preservation Environment Evaluation

Type of Decay	Risks & Metrics	Evaluation & General Comments
<p>Natural Aging Chemical decay of organic materials</p>	<p>RISK</p> <p>TWPI = 43</p>	<p>Accelerated rate of chemical decay in all organic materials due to the cumulative effects of temperature and humidity, with especially high risk for fast decaying organic materials such as acidic paper, color photographs and cellulosic plastics.</p>
<p>Mechanical Damage Physical damage to hygroscopic materials</p>	<p>GOOD</p> <p>% DC = 0.41 % EMC min = 8.6 % EMC max = 10.1</p>	<p>Minimal risk of physical damage to most hygroscopic materials such as paintings, rare books and furniture.</p>
<p>Mold Risk Mold growth in area or on collection objects</p>	<p>GOOD</p> <p>MRF = 0</p>	<p>Minimal risk of mold growth.</p>
<p>Metal Corrosion Corrosion of metal components or objects</p>	<p>OK</p> <p>% EMC max = 10.1</p>	<p>Generally OK, but archeological or salt-encrusted metals may corrode due to extended periods of moderately high levels of humidity.</p>

Graphs



Statistics

Temperature		Relative Humidity		Dew Point	
T °F Mean	67.3	%RH Mean	50	DP °F Mean	47.8
T °F Median	68	%RH Median	48	DP °F Median	47.9
T °F Stdev	2.4	%RH Stdev	7	DP °F Stdev	2.5
T °F Min	61.8	%RH Min	35	DP °F Min	41.4
T °F Max	76	%RH Max	78	DP °F Max	60.4