


Preservation Environment Evaluation

Type of Decay	Risks & Metrics	Evaluation & General Comments
Natural Aging Chemical decay of organic materials	<div style="background-color: #800000; color: white; text-align: center; padding: 2px;">RISK</div> TWPI = 38	Accelerated rate of chemical decay in all organic materials due to the cumulative effects of temperature and humidity, with especially high risk for fast decaying organic materials such as acidic paper, color photographs and cellulosic plastics.
Mechanical Damage Physical damage to hygroscopic materials	<div style="background-color: #4CAF50; color: white; text-align: center; padding: 2px;">GOOD</div> % DC = 0.23 % EMC min = 8.7 % EMC max = 9.6	Minimal risk of physical damage to most hygroscopic materials such as paintings, rare books and furniture.
Mold Risk Mold growth in area or on collection objects	<div style="background-color: #4CAF50; color: white; text-align: center; padding: 2px;">GOOD</div> MRF = 0	Minimal risk of mold growth.
Metal Corrosion Corrosion of metal components or objects	<div style="background-color: #808080; color: white; text-align: center; padding: 2px;">OK</div> % EMC max = 9.6	Generally OK, but archeological or salt-encrusted metals may corrode due to extended periods of moderately high levels of humidity.

Graphs




Statistics

Temperature		Relative Humidity		Dew Point	
T °F Mean	70	%RH Mean	50	DP °F Mean	50.2
T °F Median	69.9	%RH Median	51	DP °F Median	50.6
T °F Stdev	0.8	%RH Stdev	4	DP °F Stdev	2.2
T °F Min	68	%RH Min	37	DP °F Min	43.2
T °F Max	72.9	%RH Max	56	DP °F Max	55.6

Preservation Environment Evaluation

Type of Decay	Risks & Metrics	Evaluation & General Comments
Natural Aging Chemical decay of organic materials	OK TWPI = 45	Generally OK, but fast decaying organic materials such as acidic paper, color photographs and cellulosic plastics will be at elevated risk due to the cumulative effects of temperature and humidity
Mechanical Damage Physical damage to hygroscopic materials	GOOD % DC = 0.09 % EMC min = 8.6 % EMC max = 9	Minimal risk of physical damage to most hygroscopic materials such as paintings, rare books and furniture.
Mold Risk Mold growth in area or on collection objects	GOOD MRF = 0	Minimal risk of mold growth.
Metal Corrosion Corrosion of metal components or objects	OK % EMC max = 9	Generally OK, but archeological or salt-encrusted metals may corrode due to extended periods of moderately high levels of humidity.

Graphs



Statistics

Temperature		Relative Humidity		Dew Point	
T °F Mean	68.5	%RH Mean	47	DP °F Mean	47.6
T °F Median	68.3	%RH Median	48	DP °F Median	48
T °F Stdev	0.6	%RH Stdev	3	DP °F Stdev	2
T °F Min	65.7	%RH Min	36	DP °F Min	42
T °F Max	75.2	%RH Max	55	DP °F Max	58.1