
Preservation Environment Evaluation

Type of Decay	Risks & Metrics	Evaluation & General Comments
Natural Aging Chemical decay of organic materials	RISK TWPI = 43	Accelerated rate of chemical decay in all organic materials due to the cumulative effects of temperature and humidity, with especially high risk for fast decaying organic materials such as acidic paper, color photographs and cellulosic plastics.
Mechanical Damage Physical damage to hygroscopic materials	GOOD % DC = 0.05 % EMC min = 9.2 % EMC max = 9.4	Minimal risk of physical damage to most hygroscopic materials such as paintings, rare books and furniture.
Mold Risk Mold growth in area or on collection objects	GOOD MRF = 0	Minimal risk of mold growth.
Metal Corrosion Corrosion of metal components or objects	OK % EMC max = 9.4	Generally OK, but archeological or salt-encrusted metals may corrode due to extended periods of moderately high levels of humidity.

Graphs



Statistics

Temperature		Relative Humidity		Dew Point	
68.6	%RH Mean	51	DP°F Mean	49.6	
68.7	%RH Median	50	DP°F Median	49.4	
0.3	%RH Stdev	1	DP°F Stdev	0.7	
67.4	%RH Min	47	DP°F Min	48.1	
69.9	%RH Max	56	DP°F Max	52.3	
	68.7 0.3 67.4	68.7 %RH Median 0.3 %RH Stdev 67.4 %RH Min	68.7 %RH Median 50 0.3 %RH Stdev 1 67.4 %RH Min 47	68.7 %RH Median 50 DP °F Median 0.3 %RH Stdev 1 DP °F Stdev 67.4 %RH Min 47 DP °F Min	